



Product Information Flyer

DESCRIPTION

CIMTECH 46C is a moderate duty synthetic metalworking fluid is specifically designed for carbide grinding applications. It is also recommended for machining and grinding operations of ferrous metals.

APPLICATION

CIMTECH 46C can also be used to machine and grind cemented carbide, thermal spray coatings, cast iron, nodular iron, carbon steels and tool steels. It should not be used on magnesium alloys or non-ferrous materials.

FEATURES & BENEFITS

SUPERIOR COBALT CORROSION INHIBITION:

CIMTECH 46C is designed to maintain low levels of dissolved cobalt in the mix.

RANCIDITY CONTROL:

Excellent fluid life, minimizing the need for additives.

FOAM CONTROL:

CIMTECH 46C has excellent foam control.

CORROSION PROTECTION:

Outstanding rust protection for the work-piece and machine tool.

RECOMMENDED STARTING DILUTIONS

CIMTECH 46C is to be mixed with water for use. Always add concentrate to water. Fluid may be more difficult to mix when water temperature is below 55°F (13°C). Add no other materials to the concentrate or mix unless approved by your CIMCOOL® Territory Manager.

Grinding	5% - 10%	(1:20 to 1:10)
Machining	5% - 10%	(1:20 to 1:10)

CONCENTRATION

BCG Titration, Total Alkalinity, CIMCHEK™ Test Strip or Refractometer can be used.

The Refractometer Factor is 1.9

Multiply the scale reading obtained on your CIMCOOL® Refractometer by this factor to obtain the mix concentration in percent. Calibrate the refractometer so that it reads 0.0 with water before testing the sample mix. Remove gross contaminants from the sample mixes before testing. A refractometer is only recommended for use in checking the concentration on a fresh charge.

TYPICAL PHYSICAL AND CHEMICAL PROPERTIES

Physical State: Liquid

Solubility in water: 100% miscible

Viscosity (SUS) @ 100°F (38°C): 40

pH Concentrate: 10.3

Total Chlorine/Chloride, wt%: 0.0/0.1

Silicones: None

Appearance and Odour: Clear/Chemical

Weight, lb/gal, 60°F (15.6°C): 9.0

Flash Point /Sp.Gr./Boiling Point: SEE MSDS

pH Mix 5%, Typical Operating: 9.1

Total Sulfur, wt%: 0

HANDLING and STORAGE

If frozen, product separates. Thaw completely at room temperature and stir thoroughly before use. Inside storage is recommended.

SAFETY DATA SHEET

Available at www.cimcool.ca

For additional information refer to its WHMIS MSDS, website or contact CIMCOOL® Technical Services at 1-513-458-8199 in Ohio or 1-888-254-1919 in Canada.

Limitation of Liability: Under no circumstances, shall we or any affiliate of ours have any liability whatsoever for loss of use, or for any indirect or consequential damages. Minor formulation changes or normal variations in the manufacture of this product may cause slight variances in the data presented on this sheet.